



Test Report

NO.: ASZ0901126708T

Date: Jan 16, 2009

Page 1 of 3

Customer: Xiamen E-thing Multi-commercial Corp.

Address: Suite B, 14th Floor, Tower2, Xiangjiang Garden, Xiamen, China

Report on the submitted sample said to be

Sample name: Tennis shoes

Model: AT6010

Item/Lot No.: WS0901

Material: /

Buyer: WEE SQUEAK BABY PRODUCTS CO.

Supplier: /

Manufacturer: XIAMEN E-THING

Country of Origin: CHINA

Country of Destination: USA

Labelled Age Grading: 1-3 ages

Sample received date: Jan 12, 2009

Testing period: From Jan 12, 2009 to Jan 16, 2009

Testing Requested:

As specified by client, to determine the Lead content in the submitted sample in accordance with Consumer Product Safety Improvement Act of 2008 (H.R. 4040) section 101--Prohibition on sale of certain products containing lead.

Test method:

Testing Item	Test Method	Measuring instrument
Lead (Pb)	EPA 3050B or Acid Dissolution or EPA 3052	ICP-OES

Conclusion: The submitted sample complied with the requirement.

*****FOR FURTHER DETAILS, PLEASE REFER TO THE FOLLOWING PAGE (S)*****

Signed for AOV Ltd.

Written by Tina

Inspected by Wally

Approved by Jeanah

This Test Report is issued by the Company subject to its Conditions of Issuance of Test Report printed overleaf or attached. The results shown in this Test Report refer only to the sample(s) tested unless otherwise stated and such sample(s) are retained for 30days only. This Test Report shall not be reproduced expected in full, without written approval of the Company.

Shenzhen AOV Testing Technology Co., Ltd.

2-6/F, No.5, Yuantou Lane, Tanglang, Taoyuan Street, Nanshan District, Shenzhen, Guangdong, China

Tel: 86-755-8600 8000 Fax: 86-755-8600 8282

Http: //www.aovt.com



Test Report


NO.: ASZ0901126708T

Date: Jan 16, 2009

Page 2 of 3

Test Flow:

To Determine Lead Content:



Test Results:

Total lead content in substrate material

Element	Unit	MQL	Limit	1	2	3	4	5	6
Total lead	mg/kg	2	600#	N.D.	N.D.	28.1	94.8	N.D.	N.D.

Element	Unit	MQL	Limit	7	8	9	10	11
Total lead	mg/kg	2	600#	15.1	83.3	N.D.	32.1	24.6

Note:

- # The limit is 600ppm, after Feb 10, 2009
- The limit is 300ppm, after Aug 14, 2009
- The limit is 100ppm, after Aug 14, 2011

Specimen Description:

No.	Description	No.	Description
1	Canvas upper-navy blue	7	metal rivets-navy blue
2	Canvas upper-brown	8	metal rivets-brown
3	PU trim aside-white	9	Lining
4	PU trim aside-light pink	10	Insole
5	Lace-white	11	Outsole
6	Lace-light pink	/	/

Note:

- Specimens, which requested to determine Lead Content, have been dissolved completely.
- mg/kg = ppm
- N.D. =Not Detected (<MQL)
- MQL=Method Quantitation Limit
- Photo is included.

This Test Report is issued by the Company subject to its Conditions of Issuance of Test Report printed overleaf or attached. The results shown in this Test Report refer only to the sample(s) tested unless otherwise stated and such sample(s) are retained for 30days only. This Test Report shall not be reproduced expected in full, without written approval of the Company.

Photographs of Samples



Tennis shoes

End of Report

This Test Report is issued by the Company subject to its Conditions of Issuance of Test Report printed overleaf or attached. The results shown in this Test Report refer only to the sample(s) tested unless otherwise stated and such sample(s) are retained for 30days only. This Test Report shall not be reproduced expected in full, without written approval of the Company.